



# Test Report

Report No.: DGC171103017T01

Page 1 of 3

**Applicant** : PRIOR OUTDOOR CO., LIMITED

**Address** : YIWU CITY, ZHEJIANG, CHINA

**The following sample(s) was/were submitted and identified on behalf of the client as:**

**Product Name** : FABRIC OF THE YOGA HAMMOCK

**Model** : P-YH-01

**Brand** : PRIOR FITNESS

**Manufacturer** : PRIOR OUTDOOR CO., LIMITED

**Address** : YIWU CITY, ZHEJIANG, CHINA

**Date of Sample Received** : Nov. 03, 2017

**Test period** : Nov. 03, 2017 - Nov. 08, 2017

**Test requested** : As specified by client, to determine Breaking strength test and Colour fastness to laundering with the submitted sample.

**Test method** : Please refer to next page.

**Test result** : Please refer to next page.

**Tested by:**

*Carson*

**Reviewed by:**



**Approved by:**

*Richard*

**Date:**

Nov. 08, 2017

This document cannot be reproduced except in full, without prior written approval of NTEK. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**NTEK Testing Technology Co., Ltd.**

**Address:** No.345, Baima Block, Guantai Road, Nancheng District, Dongguan, Guangdong, China

**Tel:** (+86-769) 23301666

**Fax:** (+86-769) 23301600

**Email:** [service@ntek.org.cn](mailto:service@ntek.org.cn)

**http:** [www.dgntek.org.cn](http://www.dgntek.org.cn)

# Test Report

Report No.: DGC171103017T01

Page 2 of 3

## Test Result:

### Breaking Strength Test (Grab Test) ( ASTM D 5034-09(2017) )

Sample Description	Yellow cloth	
Test Conditions	Detection Environmental: 20℃, 65% R-H; Sample width:100mm Gauge length: 75 mm; Stretching speed: 300 mm/min;	
Test Results / N	Lengthwise	332
	Crosswise	311
Remark: The test result is the maximum force at sample break down point.		

### Colour fastness to laundering (AATCC 61-2013)

Sample Description		Yellow cloth
Test method		1A
Test result (grade):		
Change in color		4.5
Staining on Multi-fiber Stripe:	Acetate	4.5
	Cotton	4.5
	Nylon	4.5
	Polyester	4.5
	Acrylic	4.5
	Wool	4.5
Remark: Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.		

Note: The test results or data in this report will be used only for education, scientific research, enterprise product development and internal quality control or other purposes.

This document cannot be reproduced except in full, without prior written approval of NTEK. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**NTEK Testing Technology Co., Ltd.**

Address: No.345, Baima Block, Guantai Road, Nancheng District, Dongguan, Guangdong, China

Tel: (+86-769) 23301666

Fax: (+86-769) 23301600

Email: [service@ntek.org.cn](mailto:service@ntek.org.cn)

<http://www.dgntek.org.cn>

# Test Report

Report No.: DGC171103017T01

Page 3 of 3

**Photograph of Sample:**



\*\*\*End of Report\*\*\*

This document cannot be reproduced except in full, without prior written approval of NTEK. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**NTEK Testing Technology Co., Ltd.**

Address: No.345, Baima Block, Guantai Road, Nancheng District, Dongguan, Guangdong, China

Tel: (+86-769) 23301666

Fax: (+86-769) 23301600

Email: [service@ntek.org.cn](mailto:service@ntek.org.cn)

<http://www.dgntek.org.cn>